



SPC 1000 FLEXICOAT- SPORT COAT

Water-based Coating for the Sport Track.



USES

- Sport courts and recreational areas, bicycle lanes, walkways, sidewalks.
- Anti-slip floor coating, Pool decks, patios and porches.

FEATURES

- Water based system. Easy to apply.
- Surface finishes can be smooth or with abrasive material added separately.
- UV resistance, Good adhesion, can withstand water soaking.

APPLICATION METHOD

- Please ensure that the surface is sound, cohesive, clean, dry and free of dust.
- It is important to prime the surface before application. use acrylic type primers only.
- Smooth concrete surface needs to be roughen to allow for proper adhesion.
- No priming required for newly laid bituminous surface.
- Metal surface need to apply **COROCCOAT X1 Anti-Corrosion Coating**.
- For better shock absorbing, apply **DPC DAMPPROOF COATING** in **3 coats** to **1.5 mm** thick or more.
- Mix thoroughly with a mechanical stirrer at low speed before use.
- Pour and spread **FLEXICOAT SPORT** using a rubber drag any other appropriate tools to form a thin, relatively uniform.
- Let each coat to cure for 3 hours before applying the next coat.

Recommended Coverage:

- **Metal Surface:** **60 – 70 m² / 20 kg-pail** (2 layers with thickness 0.2- 0.3 mm).
0.3 kg/m²
- **Concrete Surface:** **50 – 60 m² / 20 kg-pail** (2 layers with thickness 0.4- 0.5 mm).
0.4 kg/m²

REMARKS

- It is advisable to apply **FLEXICOAT SPORT** at temperatures between 10 - 35°C .
- Do not apply if rain is expected within 24 hours.
- Ensure there is adequate ventilation during application to promote proper curing.
- Water can be added as needed **FLEXICOAT SPORT** as it may affect adhesion performance.
- Store in a cool, dry place.

WARRIOR PTE LTD

Blk 17 Marsiling Industrial Estate Road 1 # 01-11 Singapore 739279

Tel: (65) 6364 5100 / 6364 5060 / 6367 3676 Fax: (65) 6364 0629

war99@singnet.com.sg www.warrior.com.sg





SPC 1000 FLEXICOAT- SPORT COAT

Water-based Coating for the Sport Track.

TECHNICAL DATA

- Maximum aggregate size UNE EN 933-1: 1 mm.
- Curing time @ 22°C and 55% RH 24 hours for foot traffic.
- Colours Oxide Red, Green, Yellow and Grey.
- Storage Life 9 months.

PACKING:

SPC 1000 SPORT COAT 5 kg-pail, 20 kg-pail, 200 kg-drum.

SG 100 SAND GRIT 5 kg-bag, 25 kg-bag.

Disclaimer: *The information provided in this brochure is ensured to be as accurate as possible at the time of inclusion, however there may be inadvertent and occasional errors which may have slipped from our notice. Warrior Pte. Ltd does not guarantee and make no representations or warranties of any kind about the information, advice and opinions provided and reserves the right to make changes and corrections at any time, without prior notice to any parties. Warrior Pte. Ltd accepts no liability for any inaccuracies or omissions in its brochure and any decisions made based on information and opinions contained in the brochure is the sole responsibility of the user.*

WARRIOR PTE LTD

Blk 17 Marsiling Industrial Estate Road 1 # 01-11 Singapore 739279

Tel: (65) 6364 5100 / 6364 5060 / 6367 3676 Fax: (65) 6364 0629

war99@singnet.com.sg www.warrior.com.sg

